

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-103471

(43)Date of publication of application : 09.04.2002

(51)Int. CI.

B29D 30/08

B60C 5/14

C08K 7/00

C08L 23/28

(21)Application number : 2000-306297 (71)Applicant : BRIDGESTONE CORP


(22)Date of filing : 05.10.2000 (72)Inventor : OTA YASUSHI

(54) METHOD FOR MANUFACTURING PNEUMATIC TIRE AND METHOD FOR MANUFACTURING UNVULCANIZED INNER LINER MEMBER

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a method for manufacturing a pneumatic tire having simple handling of an unvulcanized inner liner member and capable of suppressing the generation of scraps.

SOLUTION: The method for manufacturing the pneumatic tire comprises the steps of coating an annular film liner 12A made of a synthetic resin on a drum 16, and coating a rubber composition liquid 20 dissolved in an industrial gasoline on the outer peripheral surface of the liner 12A. When an unvulcanized inner liner member 28 is dried, a thin annular unvulcanized inner liner member 28 having a predetermined thickness is obtained. The method also comprises the steps of removing the liner 12A from the drum 16, mounting the liner 12A on the outer peripheral surface of a tire molding drum 34, thereafter mounting a tire constituting component as prior art to complete a raw tire, and then vulcanizing the raw tire in a mold.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998, 2003 Japan Patent Office